


# FINISOL COLORATO LUCIDO

SOLVENT-BASE COLOURED POLYURETHANE  
 ALIPHATIC TOP-COATING (A+B)



## DESCRIPTION

Compound based on aliphatic polyurethane resins.

FINISOL COLORATO LUCIDO forms a film that maintains good flexibility and good resistance to abrasion and scratching; the product can be applied on metal surfaces. It resists ultraviolet rays thanks to UV filters that prevent photo-oxidative degradation.

The hardened film resists the aggression of different acids (for further details contact Sivit Technical Assistance).

Glossy appearance.

The formulation is supplied in an already colored version for some colors or in a non-pigmented version (NP15 or NP30 depending on the color required) with COLORPASTA S separately.

## USE

Painting of concrete floors.

Top-Coating for resinous coatings.

Anticorrosive finishing treatment for concrete structures and iron.

Particularly suitable for battery storage areas.

## PREPARATION OF THE SUPPORT

Each support must be cleaned, degreased and free of non cohesive parts.

Abrasive superficially to promote adhesion. It is recommended to use clear abrasive papers with grain 150 or finer. After abrasion completely remove dust from the surface.

- **Concrete surfaces and bricks** must be solid, seasoned, leveled, absorbent, not polluted by oils, powders or other substances.

Mechanically prepare the surface by sanding or grinding. Priming the surface by applying a recovery of PAVIWATER diluted with 20% by weight of water.

Any holes and slight anomalies can be repaired with PAVIRAPID or SIVITCOL

- **Ceramized surfaces** must be sanded or grinded until they are completely opaque and treated with a coat of FONDO PER PIASTRELLE.

- **Existing resin coatings** must be sanded or grinded, thus eliminating dust residues. In the case of newly made resin coatings, it is necessary to check the overcoating time of the previously applied product.

- **Metal surfaces** apply an anticorrosive epoxy primer after mechanical preparation (contact Sivit Technical Assistance).

## APPLICATION

### FINISOL COLORATO LUCIDO ALREADY IN COLOR

Combine the two components (A+B) and mix with a mixer drill for 1 minute.

Apply the mixture by roller with a consumption of about 0.130 kg/m<sup>2</sup> (for a film of about 40 microns).

To obtain a rough and non-slip surface, it is necessary to add, at the time of preparation of the 2 components, 3-5% of SFERETTE DI VETRO FINI or 10-20% of QUARZO B0/B1 (see table).

Avoid preparing partial mixtures of product to avoid errors, which could lead to a failure or incomplete hardening.

### FINISOL COLORATO LUCIDO NP + COLORPASTA S

Mix the colored paste well to homogenize.

At the time of application, add COLORPASTA S to component A and mix carefully. Add component B and mix with mixer drill for 1 minute.

Apply the mixture by roller with a consumption of about 0.130 kg/m<sup>2</sup>.

To obtain a rough and non-slip surface, it is necessary to add, at the time of preparation of the 2 components, 3-5% of SFERETTE DI VETRO FINI or 10-20% of QUARZO B0/B1 (see table).

Avoid preparing partial mixtures of product in order to avoid errors, which could lead to a failure or incomplete hardening.

**Attention:** in consideration of the nature of these types of product, particular attention should be paid during applications, in order to avoid imperfections such as rollers, overlaps, gloss differences, etc. ...In general, proceed to distribute the paint on the support homogeneously in the right quantity; when joining the newly painted area, take care to apply the painting a few centimeters away in order to discharge the excess product and then connect with the previous area by carefully dosing the quantity applied. Do not wait too long for overlaps, always paint "fresh on fresh". In the realization of large surfaces, the coordinated movement of several applicators is required.

**Warnings:** the product contains solvent, it is therefore necessary that the applicators wear the appropriate respiratory protection devices indicated on the Safety Data Sheet. It is also recommended to properly compartmentalize the work areas during application and in the following hours. During the evaporation phase, the nature of the solvents used can create annoying odors for non-experts present in nearby environments. When walkable it is recommended to ventilate the premises well.

## TECHNICAL SPECIFICATIONS

PRODUCT DATA	
Colour	Second RAL folder
Consumption	Roller: approximately 130 kg/m <sup>2</sup>
Specific gravity (at 25 °C): mixture (A+B)	0,98 +/- 0,05 g/ml
Viscosity (at 25 °C): mixture (A+B)	40-50 s (F4 Cup)
Dry residue (A+B)	66-68% by weight
VOC ready to use (Legislative Decree 161/06)	< 500 g/l Cat. A/j. Two component high performance paint (BS).
Solvent for cleaning tools	UNI Solvent
Storage	12 months, store in a dry place at a temperature between 5 °C and 30 °C; pay particular attention to component B, sensitive to air humidity
APPLICATION DATA AND TIMING	
Mixture ratio (by weight)	Already in color version: A=100, B=21 NP version: A=85, pasta=15, B=21
Pot-life (50% U.R.)	at 10°C 120 min at 25°C 90 min at 35°C 40 min
Tack Free (50% R.H.)	at 10°C 24-28 hours at 25°C 8-10 hours at 35°C 5-7 hours
Walkable (50% R.H.)	at 25°C 12-24 hours
Coverage (50% R.H.)	at 25°C da 12 a 36 ore (after sanding)
Trafficable (50% U.R.)	at 25°C 3-5 days
Hardening in depth (50% R.H.)	at 25°C 7 days
Environmental conditions of use	Temperatures between +10°C and +35°C (*)

Coating maintenance	For cleaning wait minimum 7 days from the application day
TECHNICAL PERFORMANCE DATA	
Appearance	Slightly peeled gloss
Gloss 60°	85-95 (**)
Slipperiness (D.M. 236/89)	μ>0,40 (with 3% of SFERETTE DI VETRO FINI)
Slipperiness(DIN 51130)	R11 (with 5% of SFERETTE DI VETRO GROSSE) R12 (with 20% of QUARZO B2)
Slipperiness(DIN 51097)	A (with 5% of SFERETTE DI VETRO GROSSE) C (with 10% of QUARZO B1)
Chemical resistance	Contact Sivit Technical Service for detailed information
CE marking (reg. n. 305/2011)	Complies with EN1504-2. Coating (C) Principle (PR)
Pull Off Adhesion(EN 1542)	2,1 MPa
Standard abrasion resistance EN 5470-1	<80 mg (Taber CS-10; 1000 turns; 1000 gr)
Impact resistance (EN 6272-1)	> 15 Nm
Water permeability (EN 1062-2)	w = 0,001 kg/(h <sup>0.5</sup> ·m <sup>2</sup> )

(\*) FINISOL COLORATO LUCIDO should be applied at a substrate temperature of at least 3 °C higher than the dew point to avoid adhesion problems.

(\*\*) The degree of gloss of FINISOL COLORATO LUCIDO is influenced by the following factors:  
- porosity of the support  
- film thickness

## WARNINGS

Shades of yellow, orange or some reds may require several shots to obtain a good covering effect (in some cases a first shot of white color is recommended).

Different production batches of the same color may have small differences: where possible use material from a single production batch.

Some colors based on organic pigments (red, blue, green, intense yellows, ...) tend to give up color if they are subjected to abrasion (dry or wet).

*Product for professional use, the buyer undertakes to follow the above warnings in the application of the purchased product and the instructions in the safety data sheet.*