

EPOXY BINDERS

FLUIDEPOX[®] A+B

TRANSPARENT EPOXY FORMULATION (A+B)

Solvent-free two-component epoxy primer. Multipurpose primer, it is recommended as concrete consolidating primer with high reactivity and good waterproofing. Mixed with quartz, it can also be used for realizing epoxy screeds.



Description

Two-component product based on epoxy resins used in combination with cycloaliphatic amine hardeners.

It has good penetrating and consolidating power for concrete supports.

The particular chemical structure of the amine hardener guarantees a good reactivity of the system even at low temperatures.

Use

Primer for concrete ideal for promoting adhesion and creating multilayer coatings, with roller application or by rasare. Anchoring and binder bottom to make epoxy screeds.

Impregnations of glass fibers to make fiberglass coatings. Consolidation of reinforced concrete structures and cavity filling.

Support

The substrate must have a minimum compressive strength of 25 N/mm² and a tensile strength of 1,5 N/mm²

Preparation of the support

Working on concrete bottoms it is necessary to verify that there are no rising humidity. If the concrete is newly built, you will have to wait for the complete maturation.

The surface must be solid, absorbent and free from the presence of oils, surfactants, water, dust. Any inconsistent parts will have to be removed.

Flooring must be treated mechanically, by sanding, shot peening or milling.

Applications

At the time of application, combine part A and part B in a single container and mix carefully for 2 minutes using suitable equipment (propeller drill).

Quickly use the entire contents of the container. When emptying the container, avoid scraping the edges and the bottom, as there may be some product not perfectly blended.

FLUIDEPOX can be applied in several ways:

- **as consolidant:** apply by roller or brush, pure or diluted with 5–10% ethyl alcohol or Solvent UNI
- **for simple shaving and multilayer coating:** apply a skim coat, loaded with 50% QUARZO B0 or B1
- **to make epoxy screeds:** apply at thickness, loaded with QUARZO MIX1 or MIX3
- **as repair mortar:** load the product up to 10% by weight with thickener

Consumption varies significantly according to the application methods and the substrate conditions: consult the Sivit Application Cycles for a timely and precise reference.

Warnings

For low temperature applications, the material can be heated to 25°C for easy application and catalysis (viscosity decrease).

Product for professional use. The purchaser undertakes to strictly follow the above warnings when applying the purchased product and the instructions in the safety data sheet.

FLUIDEPOX[®] A+B • Technical sheet • 05/11/2025

Sivit S.r.l.

Via Centallo 57, 10156, Torino, Italia | P.I. - C.F. 01012820013 | C.C.I.A.A. N. 478878 | Reg. Soc. Tribunale Torino N. 305/74

Sistema di gestione conforme alle ISO 9001:2015 – ISO 14001:2015 – ISO 45001:2018

commerciale@sivit.it | sivitsrl@pec.it | +39 011 273 00 33 | www.sivit.it

Technical specifications

PRODUCT DATA	
Colour	Transparent
Consumption	roller: 0,100 kg/m ² smooth: 0,350 kg/m ² of (A+B) + 0,175 kg/m ² of QUARZO B0
Specific gravity (at 25°C)	mixture (A+B): 1.10 +/- 0.05 g/ml mixture (A+B) loaded: 1,50 +/- 0,10 g/ml (with 50% QUARZO B0)
Viscosity (at 25 °C)	mixture (A+B): 470 +/- 100 mPa*s (spindle 2, rpm 60) mixture (A+B) loaded: 840 +/- 150 mPa*s (con 50% di QUARZO B0, spindle 3, rpm 60)
Viscosity with UNI Solvent (at 25°C) diluted at 10%	175 +/- 40 mPa*s (spindle 1, rpm 30)
Dry residue (A+B)	100% (approx.)
VOC ready to use (Legislative Decree 161/06)	< 200 g/l Cat.A/j. High performance twocomponent paint (BS)
Flash point	> 100°C
Solvent for cleaning tools	UNI Solvent
Storage	12 months, store in a dry place at a temperature between 5 °C and 35 °C

APPLICATION DATA AND TIMES	
Mixture ratio	by weight: A=100, B=50
Pot-life (50% R.H.)	at 10 °C > 60 min at 25 °C 30 min at 30 °C > 20 min
Dry to the touch (50% R.H.)	at 10 °C 12-16 hours at 25 °C 5-7 hours at 30 °C 2-3 hours
Walkable (50% R.H.)	at 25°C 12 hours
Coverage (50% R.H.)	at 25°C 12 to 36 hours
Trafficable (50% R.H.)	at 25°C 36 hours
Hardening in depth (50% R.H.)	at 25°C 7 days
Environmental conditions of use	Temperatures between +10°C and +30°C, R.H. < 60%, and substrate humidity < 4%. FLUIDEPOX must be applied at a substrate temperature not lower than 15°C and at least 3°C above the dew point.

PERFORMANCE TECHNICAL DATA	
Appearance	Gloss
Compressive strength (UNI 4279)	60 N/mm ²
Bending strength (UNI 7219)	40 N/mm ²
Hardness (ASTM D 2240)	78 Shore D
Chemical resistance	Contact Sivit Technical Service for detailed information
CE marking (reg. n. 305/2011)	Complies with EN13813:2004 Synthetic resin-based screed materials for use inside buildings
BCA wear resistance (EN 13892-4)	AR 0,5 (10 µm)
Adhesion force (EN 13892-8)	4,0 N/mm ²

Product for professional use. The purchaser undertakes to strictly follow the above warnings when applying the purchased product and the instructions in the safety data sheet.

FLUIDEPOX® A+B • Technical sheet • 05/11/2025

Sivit S.r.l.

Via Centallo 57, 10156, Torino, Italia | P.I. - C.F. 01012820013 | C.C.I.A.A. N. 478878 | Reg. Soc. Tribunale Torino N. 305/74

Sistema di gestione conforme alle ISO 9001:2015 – ISO 14001:2015 – ISO 45001:2018

commerciale@sivit.it | sivitsrl@pec.it | +39 011 273 00 33 | www.sivit.it