

EPOXY BINDERS

FLUIDEPOX[®] CASTING A+B

Product epoxy grouting

Solvent-free, it allows excellent adhesion on iron or concrete supports.

The low temperature reached by the mixture during hardening and its long life time mean that Fluidepox casting has a low volumetric shrinkage.

Description

Two-component epoxy product without solvents with excellent adhesion on iron and cement.

The main feature of FLUIDEPOX CASTING is the low volumetric shrinkage: this characteristic is given by the low exothermic peak value that is reached during hardening and by the long pot-life (life time of the mixture).

Use

The low exothermy of the reaction allows to realize casting masses without problems of volumetric shrinkage.

Support

The substrate must have a minimum compressive strength of 25 N/mm² and a tensile strength of 1,5 N/mm².

Preparation of the support

Concrete surfaces. they must be solid, absorbent and free from the presence of pollutants.

After abrasive the substrate, apply a FLUIDEPOX primer to saturate the porosity of the cement.

Surfaces made of ferrous material must be carefully prepared in order to eliminate calamine residues.

Application

To obtain an optimal result the material must be at a temperature around 25-30 °C.

At the time of application, combine the two components in a single container and mix carefully with a mechanical stirrer. To the mixture A+B add 80% by weight of QUARZO B0 (0.06- 0.25).

Strain the material into the volume to be filled.



Warnings

For low temperature applications, the material can be heated to 25°C for easy application and catalysis (viscosity decrease).

Product for professional use, the buyer undertakes to follow the above warnings in the application of the purchased product and the instructions in the safety data sheet.

Technical specifications

PRODUCT DATA	
Colour	Amber
Specific gravity (at 25°C): mixture (A+B)	1,05 - 1,10 g/ml
Viscosity (at 25°C): mixture (A+B)	1.200 +/- 200 mPascal
Flash point	> 170°C

Product for professional use. The purchaser undertakes to strictly follow the above warnings when applying the purchased product and the instructions in the safety data sheet.

FLUIDEPOX[®] CASTING A+B • Technical sheet • 05/11/2025

Sivit S.r.l.

Via Centallo 57, 10156, Torino, Italia | P.I. - C.F. 01012820013 | C.C.I.A.A. N. 478878 | Reg. Soc. Tribunale Torino N. 305/74

Sistema di gestione conforme alle ISO 9001:2015 – ISO 14001:2015 – ISO 45001:2018

commerciale@sivit.it | sivit srl@pec.it | +39 011 273 00 33 | www.sivit.it

APPLICATION DATA AND TIMES

Mixture ratio	A=100, B=50
Pot-life (50% R.H.)	at 15°C > 400 min at 25°C 300 min at 35°C > 180 min
Dry to the touch (50% R.H.)	at 15°C 28-36 hours at 25°C 18-24 hours at 35°C 10-14 hours
Environmental conditions of use	Temperatures between +15°C and +35°C

PERFORMANCE TECHNICAL DATA

Appearance	Liquid
Compressive strength (UNI 4279)	55 N/mm ² (after 10 days)
Bending strength (UNI 7219)	50 N/mm ² (after 10 days)
Tensile strength (ASTM D 638)	33 N/mm ² (after 10 days)

Product for professional use. The purchaser undertakes to strictly follow the above warnings when applying the purchased product and the instructions in the safety data sheet.

FLUIDEPOX[®] CASTING A+B • Technical sheet • 05/11/2025

Sivit S.r.l.

Via Centallo 57, 10156, Torino, Italia | P.I. - C.F. 01012820013 | C.C.I.A.A. N. 478878 | Reg. Soc. Tribunale Torino N. 305/74

Sistema di gestione conforme alle ISO 9001:2015 – ISO 14001:2015 – ISO 45001:2018

commerciale@sivit.it | sivitsrl@pec.it | +39 011 273 00 33 | www.sivit.it